

KAINDL Decor Chipboard P2/E1

DSP2E1 04/07-03



Áreas de uso / Aplicación

Numerosas aplicaciones con proposito de no existir cargas constantes en áreas secas para decoración interior

Construcción

Papel decorativo
Tablero Párculas P2/E1
(según EN 312)
Papel Decorativo



Medida Standard

Espesores: 8 - 38 mm

	Tab.Partículas P2/E1: standard size: (según EN 312)	2800 x 2070 mm 5600 x 2070 mm
--	---	----------------------------------

Tolerancias

	unidad	clasificación según EN 14322		Metodo test
		rango espesor <mm>		
tolerancia espesor ren relación al espesor básico:	mm	< 15		

Propiedades de la superficie

	unidad	clasificación según EN 14322	Metodo test
resistencia rasguño:	N	> 1,5	EN 14323
Imperfecciones en superficie:	mm ² /m ² mm/m ²	Imperfección puntiforme < 2 Imperfección prolata < 20	EN 14323 EN 14323
resistencia a las manchas:	grupo	≥3	EN 14323
Riesgo de agrietado:	grupo	≥3	EN 14323

resistencia a quemadura de cigarro:	grade	3 = cambio moderado en nivel de brillo y/o leves puntos marrones				EN 14323
resistencia al vapor:	grade	4 = cambio moderado en nivel de brillo y/o color				EN 14323
Decoloración (xenon arc):	grupo	> 6				EN 14323
resistencia a la abrasión:			Print Decor: Madera, Fantasia y Metalicos		Uni Decor	EN 14323
	clase		1		3A	
	IP		< 50		>150	
	rotations WR rotations		<150		>350	

Construcción: Propiedades Fisicas

	unidad	clasificación según EN13986	Metodo test
Clase Fuego: Densidad minima > 600kg/m³ Espesor minimo > 9mm		D-s2,d0	EN 13986
Vapor de agua - coeficiente de resistencia: Densidad medio 600kg/m³	μ moist μ dry	15 50	EN ISO 12572
Aislación acustica aerea:		$R = 13 \lg(m_a) + 14$	EN ISO 140-3
grado de absorción acustica: Rango frecuencia 250 a 500 Hz Rango frecuencia 100 a 2000 Hz		0,1 0,25	EN ISO 354
conductividad de calor: Densidad medio 600kg/m³	W/(m·K)	λ=0,12	EN 12664

Storage tips

Kaindl Decor Chipboards P2/E1 should always be stored flat and level.
The air temperature in storage room should be at 18-22°C, the relative air humidity at 50 to 60%.
See also Standard prCEN/TS 12872:2006

Cleaning and care

Kaindl Decor Chipboards P2/E1 are very hygienic and easy to clean.
All domestic cleaning agents can be used for cleaning Kaindl Decor Chipboards P2/E1. Do not use scouring agents.
For daily care it is only necessary to clean Kaindl Decor Chipboards P2/E1 with a damp cloth. Handle in the same way as conventional wooden boards. Sanding, sealing or polishing the surface is not necessary because of the special surface of Kaindl Decor Chipboards P2/E1.
Stubborn stains such as paint, adhesive, nail polish or oil can be cleaned off with acetone, vinegar concentrate, nail polish remover and universal thinner. In either case please use those agents sparingly, carefully and only in polluted areas.
Those agents must not stay on the surface for any length of time.
Cutting with knives directly on Kaindl Decor Chipboards P2/E1 will lead to scratches on the surface.
Always use a kind of underlay or protective mat.
Wipe off moisture around seams.

Further processing

Kaindl Decor Chipboards P2/E1 can be processed by common wood working machines.
Before processing Kaindl Decor Chipboards P2/E1 please inspect for any visible damages.
To receive a proper cut quality various measures like e.g. feed rate, pitch and geometry of the saw tooth, chip room of the saw blade, excess of the saw blade etc.

If you have any further questions please connect your salesperson or see www.kaindl.com

The recommendations and information given in this Product Sheet are to the best of our knowledge in keeping with the present state of the art.
However, they are intended purely for information purposes and as noncommittal guide-lines. As such they cannot constitute grounds for any claim under warranty.